



(19)

(11) Publication number: 01208834 A

Generated Document.

PATENT ABSTRACTS OF JAPAN

(21) Application number: 63032930

(51) Int. Cl.: H01L 21/302

(22) Application date: 17.02.88

(30) Priority:

(43) Date of application
publication: 22.08.89(84) Designated contracting
states:(71) Applicant: AGENCY OF IND SCIENCE &
TECHNOL(72) Inventor: NAKAMURA NOBUO
NAKAGAWA KIYOKAZU
KURE TOKUO

(74) Representative:


(54) ETCHING METHOD

(57) Abstract:

PURPOSE: To improve the accuracy of etching for fine working by using the mixed gas of an isotropic etching gas being represented by SF₆ and having large reactivity and an anisotropic etching gas containing heavy ions easy to be dissociated to a symmetrical shape.

CONSTITUTION: A mixed gas mainly comprising at least one kind of a gas selected from a group composed of SF₆, CF₄, NF₃, XeF₂ and F₂ as an isotropic etching gas and at least one kind of a gas (where X represents at least one kind selected from a group consisting of Cl, Br, I and H) selected from a group made up of (CXF₂)₂, (CX₂F)₂ and (CX₃)₂ is employed, and plasma etching is conducted.

Accordingly, since etching can be performed by extremely low high frequency power, a resist can be used as an etching mask, and a vertical etching hole 3 can be formed when an Si substrate 1 is etched, employing the resist 2 as the mask.



COPYRIGHT: (C)1989,JPO&Japio